



CHEMICAL ABSTRACTS®

KEY TO THE WORLD'S CHEMICAL LITERATURE®

A Publication of CHEMICAL ABSTRACTS SERVICE
Published weekly by the AMERICAN CHEMICAL SOCIETY



Best Available Copy

Editorial Office: Chemical Abstracts Service, 2540 Olentangy River Road, P.O. Box 3012, Columbus, Ohio 43210-0012 USA
Telephone 614-447-3600, Fax 614-447-3713 or 447-3709, Cable CHEMABS, Internet help@cas.org

Copyright © 2001 American Chemical Society

All Rights Reserved

Printed in the USA

Volume 135 - Number 23 - December 3, 2001

CODEN: CHABAS
ISSN: 0008-2258

Chemical Abstracts is a publication of the Chemical Abstracts Service (CAS). CAS is a member of the International Council for Scientific and Technical Information and of the National Federation of Abstracting and Information Services in the United States.

It is the careful endeavor of *Chemical Abstracts* to publish adequate and accurate abstracts of all scientific and technical papers containing new information of chemical or chemical engineering interest and to report new chemical information revealed in the patent literature, but the American Chemical Society is not responsible for omissions or for such mistakes as may be made in abstracts and index entries.

All questions regarding editorial content should be addressed to the Editorial Office, Chemical Abstracts Service, 2540 Olentangy River Road, P.O. Box 3012, Columbus, Ohio 43210-0012.

Chemical Abstracts (ISSN 0009-2258) is published the first fifty-two Mondays of the year for the prices quoted on the next page by the Chemical Abstracts Service, 2540 Olentangy River Road, P.O. Box 3012, Columbus, Ohio 43210-0012. Periodicals postage paid at Columbus, Ohio and additional mailing office. POSTMASTER: Send address changes to Customer Service Department, Chemical Abstracts Service, 2540 Olentangy River Road, P.O. Box 3012, Columbus, Ohio 43210-0012.

Library of Congress Catalog Card Number: 9-4698

The name *Chemical Abstracts*, its block design, and the insignia of the American Chemical Society are registered as trademarks with the U.S. Patent and Trademark Office. Subscribers to *Chemical Abstracts* are permitted to make royalty-free single copies of pages of *Chemical Abstracts* for use within the subscribing organization by employees or students of that organization. The preparation of multiple copies, or of copies for external distribution, or of information bulletins, bibliographies, or other compilations requires royalty payments to CAS. For more information, contact the CAS Customer Service Department, Chemical Abstracts Service, 2540 Olentangy River Road, P.O. Box 3012, Columbus, Ohio 43210-0012.

Copyright of the articles to which citations in this publication refer is held by the publishers listed at the end of the bibliographic citations, unless otherwise indicated in the original publications.

ABSTRACT SECTIONS

Biochemistry Sections

1. Pharmacology
2. Mammalian Hormones
3. Biochemical Genetics
4. Toxicology
5. Agrochemical Bioregulators
6. General Biochemistry
7. Enzymes
8. Radiation Biochemistry
9. Biochemical Methods
10. Microbial, Algal, and Fungal Biochemistry
11. Plant Biochemistry
12. Nonmammalian Biochemistry
13. Mammalian Biochemistry
14. Mammalian Pathological Biochemistry
15. Immunobiochemistry
16. Fermentation and Bioindustrial Chemistry
17. Food and Feed Chemistry
18. Animal Nutrition
19. Fertilizers, Soils, and Plant Nutrition
20. History, Education, and Documentation

Organic Chemistry Sections

21. General Organic Chemistry
22. Physical Organic Chemistry
23. Aliphatic Compounds
24. Alicyclic Compounds
25. Benzene, Its Derivatives, and Condensed Benzenoid Compounds
26. Biomolecules and Their Synthetic Analogs
27. Heterocyclic Compounds (One Hetero Atom)
28. Heterocyclic Compounds (More Than One Hetero Atom)
29. Organometallic and Organometalloidal Compounds
30. Terpenes and Terpenoids
31. Alkaloids
32. Steroids
33. Carbohydrates
34. Amino Acids, Peptides, and Proteins

Macromolecular Chemistry Sections

35. Chemistry of Synthetic High Polymers
36. Physical Properties of Synthetic High Polymers
37. Plastics Manufacture and Processing
38. Plastics Fabrication and Uses
39. Synthetic Elastomers and Natural Rubber
40. Textiles and Fibers
41. Dyes, Organic Pigments, Fluorescent Brighteners, and Photographic Sensitizers
42. Coatings, Inks, and Related Products
43. Cellulose, Lignin, Paper, and Other Wood Products
44. Industrial Carbohydrates
45. Industrial Organic Chemicals, Leather, Fats, and Waxes
46. Surface-Active Agents and Detergents

Applied Chemistry and Chemical Engineering Sections

47. Apparatus and Plant Equipment
48. Unit Operations and Processes
49. Industrial Inorganic Chemicals
50. Propellants and Explosives
51. Fossil Fuels, Derivatives, and Related Products
52. Electrochemical, Radiational, and Thermal Energy Technology
53. Mineralogical and Geological Chemistry
54. Extractive Metallurgy
55. Ferrous Metals and Alloys
56. Nonferrous Metals and Alloys
57. Ceramics
58. Cement, Concrete, and Related Building Materials
59. Air Pollution and Industrial Hygiene
60. Waste Treatment and Disposal
61. Water
62. Essential Oils and Cosmetics
63. Pharmaceuticals
64. Pharmaceutical Analysis

Physical, Inorganic, and Analytical Chemistry Sections

65. General Physical Chemistry
66. Surface Chemistry and Colloids
67. Catalysis, Reaction Kinetics, and Inorganic Reaction Mechanisms
68. Phase Equilibria, Chemical Equilibria, and Solutions
69. Thermodynamics, Thermochemistry, and Thermal Properties
70. Nuclear Phenomena
71. Nuclear Technology
72. Electrochemistry
73. Optical, Electron, and Mass Spectroscopy and Other Related Properties
74. Radiation Chemistry, Photochemistry, and Photographic and Other Reprographic Processes
75. Crystallography and Liquid Crystals
76. Electric Phenomena
77. Magnetic Phenomena
78. Inorganic Chemicals and Reactions
79. Inorganic Analytical Chemistry
80. Organic Analytical Chemistry

ISSUE INDEXES

Keyword Index
Patent Index
Author Index

purification, by blowing an inert gas. Preferably, the specifications of the ceramic plates for filtration are 10–30 ppi for the 1st stage, 40–50 ppi for the 2nd stage, and 30–40 ppi for the 3rd stage; the thickness of the fluxes in both stages is 5–8 mm; the pulse frequency in the gas purification process is 20–50 Hz; and the pore size of the blowing plug for gas purification is 10–100 μm . The title process can effectively reduce the contents of H and oxide inclusions.

135: 333991p Manufacture of bulk zirconium and neodymium based amorphous alloys by spray casting. Xu, Min; Sun, Wensheng; Zhang, Fengjun; Qian, Mingxiu (Metal Institute, Chinese Academy of Sciences, Peop. Rep. China) Faming Zhuanli Shenqing Gongsi Shoomingshu CN 1,300,883 (Cl. C22O1/00), 27 Jun 2001, Appl. 99,122,647, 17 Dec 1999; 8 pp. (Ch). The Zr or Nd alloy is manufactured by melting the component metals in an elec. arc furnace in Ar under electromagnetic stirring for 2–3 times to obtain a master alloy, placing the master alloy in a quartz cylinder with a nozzle, melting the master alloy in the quartz cylinder in vacuum (10^{-4} – 10^{-3} torr) by induction heating, and spraying the obtained melt through the quartz nozzle with Ar at 0.2–1.5 kg/cm² into a Cu mold.

135: 333992q Apparatus for heat treatment of aluminum melt in vacuum or inert gas. Nakamura, Masatomo; Sato, Kenjiro; Matsubara, Hirokazu (Daido Special Steel Co., Ltd., Japan) Jpn. Kokai Tokkyo Koho JP 2001 300,988 (Cl. B22D1/00), 30 Oct 2001, Appl. 2000/122,172, 24 Apr 2000; 4 pp. (Japan). A melt treatment apparatus has a tank for storing a melt under an atm. pressure and a treatment tank in which the melt supplied through a channel provided in the bottom of the storing tank is heated in vacuum or inert gas. The app. comprises a check valve that can close and open the melt supply channel, a gas supply pipe for blowing gas into the melt, a detector for detecting the gas pressure inside the gas supply pipe, and a valve control circuit which outputs a valve closure command to the drive mechanism operating the valve when the pressure detected by the gas detector exceeds the preset pressure. A drop in the melt depth in the storing container to below the prescribed level is prevented, and the treatment container is reliably isolated from the atm.

135: 333993r Refining of high purity Fe–Ni alloy suitable for etching in manufacture of shadow mask. Fujimoto, Kaoru (Hitachi Metals, Ltd., Japan) Jpn. Kokai Tokkyo Koho JP 2001 803,123 (Cl. C2107/00), 31 Oct 2001, Appl. 2000/125,878, 26 Apr 2000; 4 pp. (Japan). The alloy (contg. Ni 20–80%, Fe bal.) is refined and de-oxidized by vacuum induction melting with Ar gas blown into the molten metal. Preferably, Al deoxidizer (<0.1 kg/t) and other deoxidizers (<0.1 kg/t \times equiv. ratio to Al) are added before the termination of Ar gas blowing.

135: 333994s Separation of iron and copper from iron–copper alloy by applying magnetic field. Asai, Shigeo; Sung, Mun Gyu; Chino, Yasumasa (Nagoya University, Japan) Jpn. Kokai Tokkyo Koho JP 2001 303,146 (Cl. C22B9/02), 31 Oct 2001, Appl. 2000/127,135, 27 Apr 2000; 6 pp. (Japan). The process comprises stirring and applying strong magnetic field to the Fe–Cu melt during its solidification process (melt, solid and liq. coexisting state, solidified state). Preferably, the stirring force is ≥ 100 W/torr; and the magnetic field is ≥ 5 T. The title process can be used for removal of impurities.

135: 333995t Die with ceramic coating modified by ion implantation for die casting and manufacture of die-cast products. Yamazaki, Hiroshi; Negishi, Hiroaki (Olympus Optical Co., Ltd., Japan) Jpn. Kokai Tokkyo Koho JP 2001 300,710 (Cl. B22D17/22), 30 Oct 2001, Appl. 2000/125,825, 26 Apr 2000; 8 pp. (Japan). A die for die casting comprises ≥ 1 movable core linked to the movement of the die. The core has a protrusion for forming a recess in a die-cast product obtained by pouring a molten metal into a cavity into which the core is inserted. At least the protruding portion of the die is coated with a ceramic layer modified by ion implantation. The die is used for casting Al alloys, Mg alloys, or Zn alloys.

135: 333996u Casting of Fe–Ni alloy ingot for shadow mask application. Fujimoto, Kaoru; Hara, Kenichiro (Hitachi Metals, Ltd., Japan) Jpn. Kokai Tokkyo Koho JP 2001 300,694 (Cl. B22D7/00), 30 Oct 2001, Appl. 2000/122,789, 24 Apr 2000; 4 pp. (Japan). The ingot that is to be rolled into thin sheet for etching is obtained by casting the molten alloy (Ni 20–80%, Fe bal.) of $>1600^\circ\text{C}$ into an ingot mold. Preferably, a shallow ingot mold that weighs ≥ 1.1 of the wt. of the molten alloy is used. The process improves the etching evenness of the thin sheet due to existence of columnar crystals.

135: 333997v Furan no-bake foundry binders for sand molds and cores. Chang, Ken K.; Hutchings, David A. (Ashland Inc., USA) PCT Int. Appl. WO 01 81,024 (Cl. B22C1/22), 1 Nov 2001, US Appl. 559,766, 27 Apr 2000; 22 pp. (Eng). The furan cold-hardening (no-bake) binders for sand molds and cores contain: (a) reactive furan resin at nominally 1–50 parts by wt.; (b) furfuryl alc. at 10–80 parts; (c) hardener based on Lewis acid catalyst, and optionally conventional furan–resin catalyst; and (d) optional polyol at 0.1–30 parts (esp. resorcinol at 0.1–20 parts), bisphenol at 1–30 parts, and/or organosilane (as coupling agent) at 0.01–10 parts. The Lewis acid catalyst is preferably Zn chloride, and the conventional furan catalyst is a sulfonic acid at the wt. ratio of 1:8 to 8:1. The fresh resin-bonded sand mix is hardened in a pattern box for mold manuf., removed, and used as foundry mold for casting of molten metal. The cold-hardening binder shows decreased emission of vapor products from the molds and cores in casting of gray iron and steel.

135: 333998w Single crystal nickel-based heat-resistant alloys, and gas turbine blades made of same alloys. Okada, Ikuro; Takahashi, Koji; Izutsu, Daijuke; Kawai, Hisataka (Mitsubishi Heavy

Industries, Ltd., Japan) Jpn. Kokai Tokkyo Koho JP 2001 294,959 (Cl. C22C19/08), 26 Oct 2001, Appl. 2000/115,164, 17 Apr 2000; 8 pp. (Japan). The single crystal is Ni alloys contg. Cr 7.5–10, Co 4.5–6, Mo 0.5–3, W 7–8, Al 4.5–6.5, Ta 5.5–7.0, and C 0.005–0.07 and/or B 0.001–0.006 wt.%. The alloys may further contain ≥ 1 selected from 0.01–0.2 wt.% Hf, 0.01–2 wt.% Re, 0.01–0.03 wt.% Pt, 1–100 ppm Ca, 1–100 ppm Mg, and 0.5–2 wt.% of Ti. Gas turbine blades made of the Ni alloys are also claimed. The alloys show high strength at high temp. and can be prepd. by monodirectional casting.

135: 333998x Aluminum alloy ingots showing excellent thermal conductivity. Kitapka, Sanji (Nippon Light Metal Co., Ltd., Japan) Jpn. Kokai Tokkyo Koho JP 2001 294,982 (Cl. C22C21/00), 26 Oct 2001, Appl. 2000/110,228, 12 Apr 2000; 4 pp. (Japan). The Al alloy ingots contain 1.0–6.0 wt.% of Ni and <1.0 wt.% (for each) of other elements, wherein ≥ 20 atom% of the alloy is occupied by Al–Ni eutectic ppts. The Al alloy ingots may contain Ni 1.0–6.0, Si 0.1–0.6, Mg 0.2–0.8, Fe 0.1–0.8, and optionally Ti 0.005–0.15 and/or B 0.0001–0.05 wt.%. The ingots are suitable for heat sinks for elec. devices.

135: 334000b Aluminum alloy plates showing high crush resistance, and their preparation. Annap, Masamichi; Takagi, Yasuo; Takasue, Osamu (Toyota Motor Corp.; Kobe Steel, Ltd., Japan) Jpn. Kokai Tokkyo Koho JP 2001 294,985 (Cl. C22C21/06), 26 Oct 2001, Appl. 2000/110,884, 12 Apr 2000; 7 pp. (Japan). The Al alloy plates contain Si 0.4–0.8, Mg 0.4–0.8, Fe ≤ 0.3 , and Mn ≤ 0.3 wt.%, and satisfy $r_1 =$ grain size in the plate thickness direction of a cross section along with the rolling direction; $r_2 =$ grain size in the rolling direction; $av, r_1 \leq 100 \mu\text{m}$; $r_2/r_1 \geq 2$ (as av.). The Al alloy plates satisfying the grain size are press formed and aging treated to give members having ≥ 230 MPa yield strength. Alternatively, Al alloy plates of the compn. are press formed and aging treated to give members satisfying the grain size and having ≥ 230 MPa yield strength. The plates are suitable for automobile parts.

135: 334001c Chromium–nickel–iron alloys with high corrosion resistance at high temperature, and parts made of same alloys. Totani, Toshimitsu (Mitsubishi Heavy Industries, Ltd., Japan) Jpn. Kokai Tokkyo Koho JP 2001 294,987 (Cl. C22C27/06), 26 Oct 2001, Appl. 2000/109,729, 11 Apr 2000; 6 pp. (Japan). The alloys contain Ni 17–23, Cr 45–55, impurities of Si and Mn ≤ 0.4 wt.% (as total), and balance Fe. The alloys may further contain 0.5–2 wt.% of W or 1.0–3 wt.% of Co. Corrosion resistant parts made of the alloys used in high-temp. corrosive environment are also claimed. The parts are suitable for boilers in power generation plant.

135: 334002d Precipitation-hardened aluminum-based alloy with excellent fatigue strength under average tensile stress. Iwano, Hajime; Sugimoto, Yoshihiko; Iwanaga, Shogo; Seguchi, Takeshi; Suzuki, Takamasa; Suzuki, Yoshinori (Toyota Central Research and Development Laboratories, Inc.; Toyota Motor Corp., Japan) Jpn. Kokai Tokkyo Koho JP 2001 303,183 (Cl. C22O21/02), 31 Oct 2001, Appl. 2000/127,881, 27 Apr 2000; 5 pp. (Japan). The Al alloy having pptn. hardening Al phase contains Ti 0.1–0.3, Si 4–12, Cu 0–1, Mg 0–0.5 (≈ 0), Fe 0–0.7, and Mn 0–0.7%. The alloy may be a cast alloy for cylinder heads of automotive engines.

135: 334003e Ti–Ni alloy with shape memory and formability suitable for microactuators. Ishida, Akira; Miyazaki, Shuichi (Japan) U.S. Pat. Appl. Publ. US 2001 85,236 (Cl. 148–402; C22C14/00), 1 Nov 2001, JP Appl. 1998/65,898, 16 Mar 1998; 11 pp. (Eng). The shape-memory alloy contains 50–66 at.% of Ti with Ni as the balance, shows ductility $\geq 15\%$ at room temp., and can be prepd. as an amorphous brittle film by conventional vapor deposition. The ductile shape-memory alloy is obtained by: (a) crystal, of amorphous Ti–Ni alloy deposit for <1 h at 800–900 K; and (b) slow cooling to room temp. to prevent the pptn. of Ti₂Ni phase on grain boundaries.

135: 334004f Nickel microalloyed with Mg and Al for thermionic cathodes of cathode-ray tubes. Roquais, Jean-Michel; Poret, Fabian; Le, Dore Regine (Thomson Licensing S.A., Fr.) Eur. Pat. Appl. EP 1,152,447 (Cl. H01J1/42), 7 Nov 2001, FR Appl. 2000/5,806, 26 Apr 2000; 9 pp. (Eng). The Ni alloy for manuf. of cathodes in cathode-ray tubes is microalloyed with 0.01–0.1% Mg, and a controlled amt. of Al (asp. 0.01–0.02%) selected for good adhesion of emissive oxide layer to the alloy base. The typical microalloyed Ni with good adhesion of oxide layer contains 0.02% Mg and 0.005% Al, vs. occasional adhesion problems at 0.04% Mg and 0.02% Al.

135: 334005g Solid free-form fabrication of articles by upward spraying of molten metal droplets on a substrate. White, Dawn Robert; Wilcox, Daniel Edward; Subramaniam, Sankaran (Ford Global Technologies, Inc., USA) U.S. Pat. 6,306,467 (Cl. 427–470; B05D1/36), 23 Oct 2001, Appl. 332,437, 14 Jun 1999; 5 pp. (Eng). The free-form article is fabricated by: (a) providing a suitable stable substrate; (b) forming molten metal or alloy droplets, esp. by melting of wire feed; and (c) precision spraying the molten droplets upward against the substrate, for deposition and solidification to form a net-shape article. The molten droplets are typically flattened upon impact with the substrate, and are solidified with a smooth surface finish. The upward stream of molten droplets is typically generated by elec.-arc welding torch fed with ≥ 1 wires for melting. The process is suitable for fabrication of articles without conventional melt casting in molds.

135: 334006h Composites with Mo silicides and Si carbide for heat-resistant refractory material. Gnesin, B. A.; Epelbaum, Boris Marovich; Gurzhilyants, P. A. (Institut Fiziki Tverdogo Tela RAN, Russia) Russ. RU 2,154,122 (Cl. C22C29/02), 10 Aug 2000, Appl. 98,113,544, 7 Jul 1998; No pp. given (Russ). The heat-resistant composite material contains Mo₅Si₃ and Mo₅Si₃C at 7.5–87 total, SiC 20–75, and MoSi₂

[19] 中华人民共和国国家知识产权局

[51] Int. Cl.⁷

C22C 1/00

C22C 45/00 B22D 23/00

[12] 发明专利申请公开说明书

[21] 申请号 99122647.X

[43] 公开日 2001 年 6 月 27 日

[11] 公开号 CN 1300863A

[22] 申请日 1999.12.17 [21] 申请号 99122647.X

[71] 申请人 中国科学院金属研究所

地址 110015 辽宁省沈阳市沈河区文化路 72 号

[72] 发明人 徐民 孙文声 张风军 全明秀

[74] 专利代理机构 中国科学院沈阳专利事务所


代理人 张 晨

权利要求书 1 页 说明书 4 页 附图页数 2 页

[54] 发明名称 一种块体非晶态合金的制备方法

[57] 摘要

一种块体非晶态合金的制备方法,其特征在于:将母合金置于石英套筒内的石英喷嘴中;抽石英喷嘴和玻璃真空体内的真空,充入高纯氩气,反复抽真空,充氩气 2-3 遍后,保持真空体内的负压为 $10^{-2} - 10^{-3}$ Torr;通过高频感应线圈将母合金加热熔化;给石英喷嘴瞬时通入 $0.2 - 1.4 \text{ kgf/cm}^2$ 压力的高纯氩气,将母合金熔体高速瞬时铸入钢模中。本发明可以有效地提高非晶形成能力。



ISSN 1008-4274

权利要求书

1. 一种块体非晶态合金的制备方法，适用于块体非晶态合金的制备，包括 Zr 系、Nd 系等，其特征在于：首先将纯金属组元在高纯氩气保护下置于电弧炉中，采用电磁搅拌进行熔化，反复熔化 2~3 遍，制成母合金；将母合金置于石英套筒内的石英喷嘴中，用夹具将其固定，并密封夹具；通过真空抽气系统，抽石英喷嘴和玻璃真空体内的真空，当真空度达到要求时，关闭真空抽气系统，充入高纯氩气，反复抽真空、充氩气 2~3 遍后，保持真空体内的负压为 10^{-2} ~ 10^{-3} Torr；起动高频感应加热装置，通过高频感应线圈将母合金加热熔化；熔化后，通过电磁阀控制浇铸时间和气体压，给石英喷嘴瞬时通入 0.2~1.4kgf/cm² 压力的高纯氩气；由于石英喷嘴和真空体内产生很大的瞬时气压差，将母合金熔体高速瞬时铸入钢模中。
2. 按权利要求 1 所述块体非晶态合金的制备方法，其特征在于采用玻璃真空体。
3. 按权利要求 1 所述块体非晶态合金的制备方法，其特征在于：浇铸时间和气体压力采用电磁阀控制。
4. 按权利要求 1、2 所述块体非晶态合金的制备方法，其特征在于气体压力为 1.2~1.4kgf/cm²。

说明书

一种块体非晶态合金的制备方法

本发明涉及块体非晶态合金的一种制备方法，具体地讲，本发明涉及采用气压差铸入法制备块体非晶态合金。

非晶态合金具有许多优异的物理、化学和机械性能，具有晶态金属难以达到的高强度、高硬度、高延展性、高磁导率、高耐蚀性以及优异的电性能、抗辐照能力和较好的催化及贮氢能力，因而在现代工业、国防、通讯等领域都具有重要的应用价值。但是，非晶态合金的研究和应用受到其样品尺寸的限制，这是由于采用熔体急冷等制备方法制备非晶态合金时通常需要极大的冷却速度(每秒十百度以上)，这样样品在某一个方向上的尺寸必然很小，一般小于 $100\ \mu\text{m}$ 。为此，有重要实际应用的非晶态合金只能以薄带、薄片、细丝或粉末的形式制备出来，使这种材料在实际应用中受到很大限制。制备出三维块体非晶态合金已成为一项共同关注的世界难题。

近年来，在块体非晶态合金的制备方面取得了突破性进展。日本东北大学的 A. Inoue 首先在 La 基合金中制备出 3mm 厚的块体非晶。随后，美国加州理工学院的 W. L. Johnson 在 Zr 基合金中制备出 14mm 厚的块体非晶。在近几年中，以美、日、德为主的研究单位展开了大量深入的研究工作，因此近期在国际范围掀起了一个块体非晶态合金的研究热潮。最近的性能测试结果表明，Zr 基块体非晶态合金不仅具有极高的抗拉强度，而且具有与常规高合金钢相近的断裂韧性。这是十分罕见的优异性能，具有很大的应用前景。非晶态合金一般具有很低的弹性模量，因此可用作高弹性材料。用块体非晶态合金制造的高尔夫球杆端头比目前采用的 Ti 合金性能优越。块体非晶态合金的另一优点是易于加工。由于非晶态合金实际上是过冷液态，因此可采用一次近成型压力加工工艺制造出形状复杂的工件，工艺简便，成本低。另外，一些块体非晶态合金具有优异的软磁或硬磁性能，可用作磁记录和磁头材料，在通讯等方面有着很大的应用前景。

目前，块体非晶态合金的制备方法主要有：水淬、模铸、压铸、吸铸等方法。水淬法是将熔化的母合金直接淬入冷却介质中，方法简单。但由于冷却介质的阻力作用，其冷却速度较低，在很多合金系中都不易形成块体非晶态合金。水淬法制备出的合金还有两种严重的缺陷，一是形状很难控制，二是表面有氧化现象。模铸法是将熔化的母合金直接铸入金属模具中，可以显著提高母合金的冷却速度。但是由于

母合金熔体与金属模具内的压差接近，造成铸入时流速慢，导致冷却速度降低。另外，喷嘴内的合金熔体氧化现象严重。由于不同合金熔体氧化程度不同，使喷嘴底部开口直径大小很难控制，而且制备出的块体非晶也存在着表面氧化现象。压铸法和吸铸法可以避免水淬法和模铸法的缺点，但其制备装置复杂，操作复杂，成本高。

本发明的目的在于提供一种块体非晶态合金的制备方法，该方法可以有效地提高非晶形成能力。

本发明提供的制备方法，适用于块体非晶态合金的制备，包括 Zr 系、Nd 系等，其特征在于：首先将纯金属组元在高纯氩气保护下置于电弧炉中，采用电磁搅拌进行熔化，反复熔化 2-3 遍，制成母合金；将母合金置于石英套筒内的石英喷嘴中，用夹具将其固定，并密封夹具；起动真空抽气系统，抽石英喷嘴和玻璃真空体内的真空，当真空度达到要求时，关闭真空抽气系统，充入高纯氩气，反复抽真空、充氩气 2-3 遍后，保持真空体内的负压为 10^{-2} ~ 10^{-3} Torr；起动高频感应加热装置，通过高频感应线圈将母合金加热熔化；熔化后，通过氩气瓶上连接的电磁阀，控制浇铸时间和气体压力，给石英喷嘴瞬时通入一定压力（1.2~1.4kgf/cm²）的高纯氩气，由于石英喷嘴和真空体内产生很大的瞬时气压差，将母合金熔体高速瞬时铸入铜模中，形成块体非晶态合金。

本发明的关键在于浇铸温度、浇铸时间和气体压力，本发明具有下述优点：

1. 解决了水淬法和模铸法制备块体非晶态合金时的氧化问题和石英喷嘴底部开口直径大小不易控制的问题，通过反复进行的抽真空和充高纯氩气，不但避免了母合金熔体的氧化，也解决了喷嘴开口大小难以控制的问题。

2. 由于采用电磁阀控制氩气压力和氩气充入时间，可以人为调节和控制气体压力和浇铸时间。

3. 由于石英喷嘴内的母合金熔体采用石英导流管铸入铜模中，不但造成射流集中、稳定，而且减小了熔体浇铸时的喷射阻力，提高了冷却速度。

4. 母合金熔化后，由于通过电磁阀给合金熔体瞬时施加一定压力的气体，造成石英喷嘴和真空体内的瞬时气压差，使石英喷嘴内的合金熔体高速喷射铸入铜模中，提高了冷却速度，从而提高了非晶形成能力。

5. 由于真空体采用玻璃制造，所以可以通过透明的真空体清楚地观测整个浇铸过程，便于控制浇铸过程，提高块体非晶态合金制备的成功率。

6. 整个制备方法成本低，工艺简单，便于操作。

总之，通过本发明所述方法可以有效地提高合金熔体的冷却速度，成功地制备出

块体非晶态合金。采用本发明制备出的不含 Be 的 Zr-Al-Ni-Cu 块体非晶态合金的部分力学性能已达到含 Be 的高尔夫球杆端头用 Zr-Ti-Cu-Ni-Be 块体非晶的力学性能。除上述实例以外，采用本发明还成功地制备出直径是 4mm 的 $\text{Nd}_{60}\text{Al}_{15}\text{Fe}_{10}\text{Cu}_{10}\text{Co}_5$ 、 $\text{Nd}_{60}\text{Al}_{15}\text{Fe}_{10}\text{Co}_{10}\text{Cu}_5$ 和 $\text{Nd}_{60}\text{Fe}_{20}\text{Cu}_{10}\text{Al}_{10}$ 等块体非晶态合金。该方法成本低，工艺简单，便于控制 and 操作。下面通过实施例详述本发明。

附图 1 块体非晶态合金的制备原理示意图。

附图 2 $\text{Zr}_{55}\text{Al}_{10}\text{Ni}_5\text{Cu}_{30}$ 块体非晶态合金的 X 射线衍射谱。

附图 3 $\text{Zr}_{57}\text{Ti}_5\text{Al}_{10}\text{Cu}_{20}\text{Ni}_8$ 块体非晶态合金的 X 射线衍射谱。

实施例 1:

实验设备如图 1 所示，1 抽气管（接真空抽气系统和高纯氩气），2 夹具 3 石英套筒，4 石英喷嘴，5 高频感应线圈（接高频感应加热装置），6 石英导流管，7 铜模，8 可调底座，9 底板，10 玻璃真空体。

原材料为纯金属 Zr、Al、Ni、Cu，其纯度分别为：Zr99.9%；Al99.9%；Ni99.5%；Cu99.9%。将原材料按 $\text{Zr}_{55}\text{Al}_{10}\text{Ni}_5\text{Cu}_{30}$ 的原子百分比置于电弧炉中，抽真空后通入高纯氩气，采用电磁搅拌进行熔化，反复熔化 2~3 遍使合金均匀化，制成母合金。

将母合金通过本发明进行制备，模具采用 $\Phi 4 \times 60$ 和 $4 \times 30 \times 55$ 的铜模。其中，浇铸温度为：830℃~，气体压力为：1.2kgf/cm²。

通过本发明可以成功地制备出尺寸为 $\Phi 4 \times 60$ 和 $4 \times 30 \times 55$ 的 $\text{Zr}_{55}\text{Al}_{10}\text{Ni}_5\text{Cu}_{30}$ 块体非晶态合金。

X 射线衍射的实验结果如图 2 所示。

实施例 2:

所用的纯金属为 Zr、Ti、Al、Cu、Ni，其纯度分别为：Zr99.9%；Ti99.9%；Al99.9%；Cu99.9%；Ni99.5%。母合金的成分为 $\text{Zr}_{57}\text{Ti}_5\text{Al}_{10}\text{Cu}_{20}\text{Ni}_8$ （原子百分比）。模具采用 $\Phi 4 \times 60$ 和 $2 \times 30 \times 55$ 的铜模。其中，浇铸温度为：1110℃~，气体压力为：1.3kgf/cm²。其余同实施例 1。

通过本发明可以成功地制备出尺寸为 $\Phi 4 \times 60$ 和 $2 \times 30 \times 55$ 的 $\text{Zr}_{57}\text{Ti}_5\text{Al}_{10}\text{Cu}_{20}\text{Ni}_8$ 块体非晶态合金。

X 射线衍射的实验结果如图 3 所示。

比较例:

Zr 基块体非晶态合金已进入应用化阶段。美国的 W. L. Johnson 应用 Zr-Ti-Cu-Ni-Be（Be 含量超过 20%）块体非晶来生产高尔夫球杆端头，带来了巨大商业利润。

由于 Be 是一种有毒金属，含 Be 合金的生产带来很大问题，所以我们采用本发明制备出不含 Be 的 $Zr_{55}Al_{10}Ni_5Cu_{30}$ 块体非晶态合金，用以代替美国的材料，并测定了其力学性能。通过本发明制备的 Zr-Al-Ni-Cu 块体非晶和美国的 Zr-Ti-Cu-Ni-Be 块体非晶部分力学性能的结果如表 1 所示。

通过对比可以看出，两者的力学性能是非常相似的。可见采用本发明制备的不含 Be 的 Zr-Al-Ni-Cu 块体非晶态合金的部分力学性能已达到含 Be 的 Zr-Ti-Cu-Ni-Be 块体非晶的力学性能。

表 1 块体非晶态合金力学性能测试结果

力学性能	Zr-Al-Ni-Cu	Zr-Ti-Cu-Ni-Be
密度 (g/cm^3)	6.44	6.1
硬度 (kg/mm^2)	509	570
抗压强度 (GPa)	1.6	1.8
抗弯强度 (GPa)	2.7	2.8

99-12-27

说明书附图




图 1

99-1007




图 2




图 3

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.